

Europäisches Patentamt
European Patent Office
Office européen des brevets



(11) EP 0 995 786 A1

(12) EUROPEAN PATENT APPLICATION

(43) Date of publication:
26.04.2000 Bulletin 2000/17

(51) Int Cl.7: C09K 9/02, G02F 1/15

(21) Application number: 99850155.5

(22) Date of filing: 20.10.1999

(84) Designated Contracting States:
AT BE CH CY DE DK ES FI FR GB GR IE IT LI LU
MC NL PT SE
Designated Extension States:
AL LT LV MK RO SI

- Sugiyama, Izuru
Yokohama-shi, Kanagawa-ken, 231-0815 (JP)
- Kobayashi, Masaaki
Yokohama-shi, Kanagawa-ken, 231-0815 (JP)
- Imafuku, Hiroshi
Yokohama-shi, Kanagawa-ken, 231-0815 (JP)

(30) Priority: 22.10.1998 JP 30076498


(71) Applicant: Nippon Mitsubishi Oil Corporation
Minato-ku, Tokyo 105-8412 (JP)

(74) Representative: Modin, Jan et al
Ehrner & Delmar Patentbyrå AB
Box 10316
100 55 Stockholm (SE)

(72) Inventors:
• Nishikitani, Yoshinori
Yokohama-shi, Kanagawa-ken, 231-0815 (JP)


(54) Electrochromic device

(57) The electrochromic device which has an ion conductive layer obtained by curing a composition comprising (a) a bipyridinium compound represented by formula (1), (b) a specific amine compound and (c) a precursor component of a polymeric solid electrolyte, disposed between two electrically conductive substrates at least one of which is transparent, said formula (1) being



wherein X⁻ and Y⁻ are the same or different and are each independently a counter anion selected from the group consisting of an halogen anion, ClO₄⁻, BF₄⁻, PF₆⁻, CH₃COO⁻ and CH₃(C₆H₄)SO₃⁻, R¹ is hydrogen or a C₁ - C₅ alkyl group, R² is a C₁ - C₃₀ divalent hydrocarbon or oxygen-containing hydrocarbon group, R³ is a C₁ - C₂₀ hydrocarbon or oxygen-containing hydrocarbon group and a is an integer of 0 or 1.

FIG. 1



EP 0 995 786 A1

Description

[0001] This invention relates to electrochromic devices which are useful for transmission-type device such as smart windows, reflective-type devices such as antiglare mirrors for automobiles and decorative mirrors and displays. Description of the Prior Art

scription of the Prior Art

[0002] Japanese Laid-Open Patent Publication No. 63-18336 discloses a method of producing a chromogenic layer used for an electrochromic device by vacuum-depositing or sputtering an inorganic oxide such as tungsten oxide (WO_3) over a transparent electrically conductive film. However, this method leads to elevated production costs due to the involvement of technique under vacuum conditions.

[0003] It has been proposed to produce a chromogenic layer by using an electrochromic compound such as viologen

[0004] For example, Japanese Laid-Open Patent Publication No. 9-120088 discloses a solution for an electrochromic device which is obtained by dissolving an electrochromic compound such as viologen and an electron donating compound in a suitable solvent. However, this attempt has a problem that the resulting electrochromic device is deteriorated in electrochromic performances since viologen which is freely present in the solvent, is easily dimerized, leading to precipitation. Furthermore, there is a risk that the liquid medium possibly scatters upon breakage of the device.


precipitation. Furthermore, there is a risk that the liquid medium possibly scatters upon breakage of the device. [0005] Japanese Laid-Open Patent Publication No. 7-70218 discloses a solid chromogenic layer produced by dispersing an electrochromic compound such as viologen and an electron donating compound in a polymer with the aid of a monomer which can be polymerized by irradiating electromagnetic radiation. Since the solid medium is used in this chromogenic layer, there is no risk that the medium scatters upon breakage of the device. However, the viologen is still freely present even in the solid medium and thus easily precipitates by being dimerized, resulting in a failure of completely avoiding the resulting electrochromic device from being deteriorated.

[0006] Furthermore, the viologen and electron donating compound are changed in properties by ultraviolet ray penetrating through the substrate of the device, leading to the shortened lifetime thereof.


SUMMARY OF THE INVENTION

[0007] After an extensive research and study, it has been found that the foregoing problems can be overcome by an electrochromic device having a structure described below.

[0008] According to one aspect of the present invention, there is provided an electrochromic device having an ion conductive layer obtained by curing a composition containing (a) a bipyridinium compound represented by formula (1), (b) an amine compound represented by formula (2) and / or (3) and (c) a precursor component of a polymeric solid electrolyte, disposed between two electrically conductive substrates at least one of which is transparent, formula (1) being




wherein X- and Y- may be the same or different and are each independently a counter anion selected from the group consisting of an halogen anion, ClO_4^- , BF_4^- , PF_6^- , CH_3COO^- and $\text{CH}_3(\text{C}_6\text{H}_4)\text{SO}_3^-$, R^1 is hydrogen or a $\text{C}_1 - \text{C}_5$ alkyl group, R^2 is a $\text{C}_1 - \text{C}_{30}$ divalent hydrocarbon residue, R^3 is a $\text{C}_1 - \text{C}_{20}$ hydrocarbon residue and a is an integer of 0 or 1; formula (2) being



wherein R⁴ is hydrogen or a C₁ - C₅ alkyl group, R⁵ is a C₁ - C₁₅ hydrocarbon residue, b is an integer of 0 or 1, R⁶ and R⁷ may be the same or different and are each independently hydrogen or a C₁ - C₂₀ hydrocarbon residue, R⁸ is hydrogen or a C₁ - C₂₀ hydrocarbon residue and Ar¹ is a C₆ - C₂₀ divalent aromatic hydrocarbon residue; and formula (3) being

EP 0 995 786 A1



wherein R^9 is hydrogen or a $\text{C}_1 - \text{C}_5$ alkyl group, R^{10} is a $\text{C}_1 - \text{C}_{15}$ hydrocarbon residue, c is an integer of 0 or 1, R^{11} and R^{12} may be the same or different and are each independently hydrogen or a $\text{C}_1 - \text{C}_{20}$ hydrocarbon residue and R^{13} is hydrogen or a $\text{C}_1 - \text{C}_{20}$ hydrocarbon residue.

[0009] According to the other aspect of the present invention, there is provided an electrochromic device having the ion conductive layer obtained by curing the composition further containing (d) an ultraviolet absorbing compound having an ethylenic double bond.

BRIEF DESCRIPTION OF THE DRAWINGS

[0010] FIG. 1 is a cross-sectional view showing the structure of an electrochromic device according to the present invention.

[0011] FIG. 2 is a cross-sectional view showing the structure of an electrochromic smart window glass according to the present invention.

[0012] FIG. 3 is a cross-sectional view showing the structure of an electrochromic mirror according to the present invention.

PREFERRED EMBODIMENTS OF THE INVENTION

[0013] The electrochromic device according to the present invention is comprised of two electrically conductive substrates. The term "electrically conductive substrate" refers to a substrate having a function as an electrode. Therefore, the electrically conductive substrates used herein encompass those made from electrically conductive materials and those obtained by laminating an electrically conductive layer over one or both surfaces of a non-electrically conductive substrate. No matter whether the substrates are electrically conductive or not, it is required to have a smooth surface at normal temperature. The surface, however, may be flat or curved as well as deformable under stress.

[0014] At least one of the electrically conductive substrates is transparent and the other may be transparent or opaque or may be a reflective electrically conductive substrate which can reflect light.

[0015] Generally, a device having electrically conductive substrates both of which are transparent is suitable for displays and smart windows glasses. A device having a electrically conductive transparent substrate and an opaque one is suitable for displays. A device having a transparent electrically conductive substrate and a reflective one is suitable for electrochromic mirror.

[0016] The transparent electrically conductive substrate may be produced by laminating a transparent electrode layer over a transparent substrate. The term "transparent" denotes optical transmission ranging from 10 to 100 percent.

[0017] No particular limitation is imposed on a material of the transparent substrate, which may be color or colorless glasses, reinforced glasses or color or colorless transparent resins. Specific examples of such resins are polyethylene terephthalate, polyethylene naphthalate, polyamide, polysulfone, polyether sulfone, polyether etherketone, polyphe-nylene sulfide, polycarbonate, polyimide, polymethyl methacrylate and polystyrene.

[0018] The transparent electrode layer may be a metal thin film of gold, silver, chrome, copper and tungsten or an electrically conductive thin film of metal oxides. Specific examples of the metal oxides are ITO ($\text{In}_2\text{O}_3\text{-SnO}_2$), tin oxide, silver oxide, zinc oxide and vanadium oxide. The film thickness is usually within the range of 10 to 500 nm, preferably 50 to 300 nm. The surface resistance of the film is within the range of usually 0.5 to 500 Ω/cm^2 , preferably 1 to 50 Ω/cm^2 . Any suitable method of forming a transparent electrode layer may be employed depending on the type of metals and/or metal oxides constituting the electrode. The transparent electrode layer may be formed by vacuum evaporation, ion-plating, sputtering and a sol-gel method.

[0019] For the purpose of imparting oxidation-reduction capability and electric double layer capacitance and improving electric conductivity, an opaque electrode activator may be partially applied to the surface of the transparent electrode layer. The electrode activator may be a metal such as copper, silver, gold, platinum, iron, tungsten, titanium and

EP 0 995 786 A1

lithium and an organic material having oxidation-reduction capability, such as polyaniline, polythiophen, polypyrrole and phthalocyanine, a carbon material such as active carbon and graphite a metal oxide such as V_2O_5 , MnO_2 , NiO and Ir_2O_3 and a mixture thereof.

[0020] Upon forming the electrode activator over the transparent electrode layer, it is necessary not to harm the transparency thereof excessively. Therefore, the opaque electrode activator may be applied onto an electrode by forming thin stripes or dots of a composition comprising an active carbon fiber, graphite and an acrylic resin over a transparent ITO layer or forming a mesh of a composition comprising V_2O_5 , acetylene black and butyl rubber over a gold thin film.

[0021] The opaque electrically conductive substrate may be produced by substituting the transparent substrate of the above-described transparent electrically conductive substrate with an opaque substrate such as various plastics, glasses, woods and stones.

[0022] Eligible reflective electrically conductive substrates for the present invention are (1) laminates obtained by laminating a reflective electrode layer over a non-electrically conductive transparent or opaque substrate, (2) laminates obtained by laminating a transparent electrode layer over one surface of a non-electrically conductive transparent substrate and a reflective layer over the other surface thereof, (3) laminates obtained by laminating a reflective layer over a non-electrically conductive transparent substrate and a transparent electrode layer over the reflective layer, (4) laminates obtained by laminating a transparent electrode layer over a reflective plate used as a substrate and (5) plate-like substrates which themselves have functions as a photo-reflective layer and an electrode layer.


[0023] The term "reflective electrode layer" denotes a thin film which has a mirror surface and is electrochemically stable in performance as an electrode. Specific examples of such a thin film are a metal film of gold, platinum, tungsten, tantalum, rhenium, osmium, iridium, silver, nickel or palladium and an alloy film of platinum-palladium, platinum-rhodium or stainless. Any suitable method of forming such a thin film may be employed such as vacuum evaporation, ion-plating and sputtering.

[0024] The substrate to be provided with a reflective electrode layer may be transparent or opaque. Therefore, the substrate may be the above-described transparent substrate and various plastics, glasses, woods and stones which may not be transparent.

[0025] The term "reflective plate" or "reflective layer" denotes a substrate having a mirror surface or a thin film which may be a plate of silver, chrome, aluminum, stainless, nickel-chrome or a thin film thereof.

[0026] If the above described reflective electrode layer per se is rigid, a substrate may not be used.

[0027] In the present invention, a bipyridinium compound is used as an electrochromic material and represented by the formula



The bipyridinium compound is hereinafter referred to as Component (A). In formula (1), X^- and Y^- may be the same or different and are each independently a counter anion selected from the group consisting of an halogen anion, ClO_4^- , BF_4^- , PF_6^- , CH_3COO^- and $CH_3(C_6H_4)SO_3^-$. The halogen anion may be F^- , Cl^- , Br^- and I^- .

[0028] R^1 may be hydrogen or a $C_1 - C_6$ alkyl group. Specific examples of the alkyl group are methyl, ethyl, i-propyl, n-propyl, n-butyl, t-butyl and n-pentyl group. Preferred are hydrogen and methyl group.








[0029] R^2 is a $C_1 - C_{30}$ divalent hydrocarbon group. The term "hydrocarbon residue" refers to hydrocarbon groups and oxygen-containing hydrocarbon groups. The divalent hydrocarbon residues include hydrocarbon groups such as alkylene groups and divalent aromatic hydrocarbon groups as well as divalent oxygen-containing hydrocarbon groups having an ether bond, such as (poly)oxyalkylene groups. The alkylene group are those having 1 to 10, preferably 1 to 5 carbon atoms. Preferred examples of the alkylene group are methylene, ethylene, tetramethylene and propylene groups, among which methylene group is particularly preferred.

[0030] Typical examples of the divalent aromatic hydrocarbon groups are $C_6 - C_{20}$ arylene or substituted arylene groups such as m-phenylene, n-phenylene, substituted phenylene (alkyl-substituted phenylene), biphenylene and naphthylene groups, among which m-phenylene and n-phenylene are preferred.







[0031] The oxygen-containing hydrocarbon group may be $-OCH_2CH_2-$ and $-CH_2OCH_2CH_2-$.

[0032] R^3 is a monovalent hydrocarbon residue having 1 to 20, preferably 2 to 10 carbon atoms. The hydrocarbon residue includes hydrocarbon groups and oxygen-containing hydrocarbon groups. Therefore, the monovalent hydrocarbon residue encompasses hydrocarbon groups such as alkyl groups, aryl groups and aralkyl groups and alkoxy

EP 0 995 786 A1





EP 0 995 786 A1











[0036] Two or more of these compounds may be used in combination. Component (A) may be used in combination with a compound facilitating color development. The color developing compound may be bonded to Component (A).

[0037] In the electrochromic device according to the present invention, an amine compound is used as an electron-donating compound. Such an amine compound may be those represented by formula (2) and / or (3) and hereinafter referred to as Component (B):

EP 0 995 786 A1



[0038] R^4 and R^9 in formulae (2) and (3) are each independently hydrogen or a $\text{C}_1 - \text{C}_5$ alkyl group such as methyl, ethyl, i-propyl, n-propyl, n-butyl, t-butyl and n-pentyl groups. Particularly preferred are hydrogen and methyl groups. R^5 and R^{10} are each independently a $\text{C}_1 - \text{C}_{15}$ divalent hydrocarbon residue. Specific examples of the divalent hydrocarbon residue are those as represented by the following formulae:




EP 0 995 786 A1

b and c in formulae (2) and (3) are each 0 or 1.

[0039] R⁶ and R⁷ in formula (2) and R¹¹ and R¹² in formula (3) are each independently hydrogen or a hydrocarbon residue having 1 to 20, preferably 1 to 10 carbon atoms. The hydrocarbon residue encompasses hydrocarbon groups and oxygen-containing hydrocarbon groups. Specific examples of the hydrocarbon groups are an alkyl group such as methyl, ethyl, n-propyl, i-propyl, n-butyl, i-butyl, t-butyl, hexyl, heptyl and octyl groups, alkylphenyl group such as tolyl and ethylphenyl groups and an aryl group such as phenyl group and an aralkyl group. The oxygen-containing hydrocarbon group may be an alkoxyphenyl group such as methoxyphenyl and ethoxyphenyl groups.


[0040] R⁸ and R¹³ are each independently hydrogen or a hydrocarbon residue having 1 to 20, preferably 1 to 10 carbon atoms. The hydrocarbon residue encompasses hydrocarbon groups and oxygen-containing hydrocarbon groups. Specific examples of the hydrocarbon group are an alkyl group such as methyl, ethyl, n-propyl, i-propyl, n-butyl, i-butyl, t-butyl, hexyl, heptyl and octyl groups, alkylphenyl group such as tolyl and ethylphenyl groups and an aryl group such as phenyl group and an aralkyl group. The oxygen-containing hydrocarbon group may be an alkoxyphenyl group such as methoxyphenyl and ethoxyphenyl groups or an oxygen-containing hydrocarbon group represented by formula (a) or (b):



wherein R' is as defined with respect to R⁵ in formula (2) or R¹⁰ in formula (3), R is as defined with respect to R⁴ in formula (2) or R⁹ in formula (3), R'' is an alkylene group having 2 to 5, preferably 2 to 3 carbon atoms, such as ethylene, trimethylene and propylene groups, a' is an integer of 0 or 1, b' is an integer of 1 to 5, preferably 1 or 2.

[0041] Ar¹ in formula (2) is a divalent aromatic hydrocarbon group having 6 to 20, preferably 6 to 12 carbon atoms, o-phenylene, m-phenylene, p-phenylene, substituted phenylene group of which substituent may be as defined with respect to R⁵, preferably alkyl-substituted phenylene group, biphenylene and naphthylene group.

[0042] If R¹³ in formula (2) or (3) is a group of formula (a), Component (B) has carbon-carbon double bonds at the terminal ends, as represented by the formulae



wherein R¹⁸ and R¹⁹ may be the same or different and are each independently as defined with respect to R⁴ in formula (2), R¹⁹ and R²² may be the same or different and are each independently as defined with respect to R⁵ in formula (2), R²⁰ and R²¹ may be the same or different and are each independently as defined with respect to R⁶ and R⁷ in formula (2), Ar² is as defined with respect to Ar¹ in formula (2), and f and g may be the same or different and are each as defined with respect to b in formula (2), and

EP 0 995 786 A1

nyl)-N,N',N'-triphenylbenzidine, N-(4-aminophenyl)-N',N'-diphenylbenzidine, N-(4-aminophenyl)-N-tolylbenzidine, N-(4-aminophenyl)-N-phenyl-N'-tolylbenzidine, N-(4-aminophenyl)-N-tolyl-N'-phenylbenzidine, N-(4-aminophenyl)-N,N'-ditolylbenzidine, N-(4-aminophenyl)-N',N'-ditolylbenzidine, N-(4-aminophenyl)-N-phenyl-N',N'-ditolylbenzidine, N-(4-aminophenyl)-N,N'-diphenyl-N'-tolylbenzidine, N-(4-aminophenyl)-N,N',N'-tritolylbenzidine, N-(4-aminophenyl)-N-methylbenzidine, N-(4-aminophenyl)-N-phenyl-N'-methylbenzidine, N-(4-aminophenyl)-N-methyl-N-methyl-N'-phenylbenzidine, N-(4-aminophenyl)-N,N'-dimethylbenzidine, N-(4-aminophenyl)-N,N'-dimethylbenzidine, N-(4-aminophenyl)-N-phenyl-N',N'-dimethylbenzidine, N-(4-aminophenyl)-N,N'-diphenyl-N'-methylbenzidine, N-(4-aminophenyl)-N,N',N'-trimethylbenzidine, N,N,N',N'-tetramethyl-1,4-phenylenediamine and 5,10-dihydro-5,10-dimethylphenazine.





[0046] Acid halides to be used for the reaction with the above-described amine compound may be those represented by the formula











wherein R³⁶ is as defined with respect to R⁴ in formula (2) and Z is a halogen atom such as fluorine, chlorine, bromine and iodine.

[0047] Specific examples of the reactive acid halide are chloride acrylate and chloride acrylate.









[0048] Specific examples of Component (B) are as follows and may be used in combination:



EP 0 995 786 A1




EP 0 995 786 A1




50

55

EP 0 995 786 A1



EP 0 995 786 A1



[0049] The ratio of Component (B) to a precursor of polymeric solid electrolyte hereinafter described is not particularly restricted but is usually 0.01 to 20 mass percent, preferably 0.1 to 10 mass percent.


[0050] The molar ratio of Component (A) to Component (B) is usually 10/1 to 1/20, preferably 2/1 to 1/3.

[0051] The term "precursor component of a polymeric solid electrolyte" (hereinafter referred to as Component (C)) denotes a component having fluidity which can be converted to a polymeric solid electrolyte by being cured. The polymeric solid electrolyte encompasses those which are substantially solid at room temperature and those which are gelatinized and thus exhibit almost no fluidity at room temperature. Despite that the polymeric solid electrolyte is solid or gel, the ion conductivity thereof is usually greater than 1×10^{-7} S/cm, greater than 1×10^{-6} S/cm, more preferably 1×10^{-5} S/cm.

[0052] Component (C) is basically composed of a polymeric monomer and a supporting electrolyte and may further contain preferably a solvent and other components as required.


[0053] Eligible polymeric monomers are polyurethane monomers, acryloyl- or methacryloyl- modified polyalkyleneoxides, among which acryloyl- or methacryloyl- modified polyalkyleneoxides are preferred.

[0054] A polyurethane monomer having an acryloyl group or a methacryloyl group at both of the terminal ends is represented by the formula




wherein R^{37} and R^{38} may be the same or different and are each independently a group of formula (11), (12) or (13), R^{39} and R^{40} may be the same or different and are each independently a divalent hydrocarbon group having 1 to 20, preferably 2 to 12 carbon atoms, Y is a polyether unit, a polyester unit, polycarbonate unit or a mixture thereof, j is an integer of 1 to 100, preferably 1 to 50, more preferably 1 to 20;

formula (11) being




formula (12) being

EP 0 995 786 A1



and
formula (13) being



[0055] In formulae (11) to (13), R^{41} , R^{42} and R^{43} may be the same or different and are each independently hydrogen or a C_1 - C_3 alkyl group, and R^{44} is a divalent to quaternary organic residue having 1 to 20, preferably 2 to 8 carbon atoms.

[0056] Specific examples of the organic residue are hydrocarbon residues such as alkyltolyl groups, alkyltetratolyl groups and alkylene groups represented by the formula




wherein R^{45} is a C_1 - C_3 alkyl group or hydrogen, k is an integer of 0 to 6 and if k is greater than 2, R^{45} may be the same or different.

[0057] The hydrogen atoms in formula (14) may be partially substituted by an alkoxy group having 1 to 6, preferably 1 to 3 carbon atoms and an oxygen-containing hydrocarbon group such as a C_6 - C_{12} aryloxy group.

[0058] Specific examples of R^{44} are methylene group, tetramethylene group and groups represented by the following:

EP 0 995 786 A1





[0059] The divalent hydrocarbon group represented by R^{39} and R^{40} in formula (10) may be exemplified by aliphatic hydrocarbon groups, aromatic hydrocarbon groups and alicyclic hydrocarbon groups. The aliphatic hydrocarbon group may be an alkylene group represented by formula (14) above.

[0060] The divalent aromatic and alicyclic hydrocarbon groups may be exemplified by hydrocarbon groups represented by the following:








[0061] In formula (15) through (17), R^{46} and R^{47} may be the same or different and are each independently a phenylene group, a substituted phenylene group (alkyl-substituted phenylene group), a cycloalkylene group and a substituted cycloalkylene group (alkyl-substituted cycloalkylene group), and R^{48} , R^{49} , R^{50} and R^{51} may be the same or different and are each independently hydrogen or a C_1 - C_3 alkyl group and l is an integer of 1 to 5.


[0062] Specific examples of R^{39} and R^{40} in formula (10) are the following divalent group:




EP 0 995 786 A1




[0063] In formula (10), Y indicates a polyether unit, a polyester unit, a polycarbonate unit or a mixed unit thereof. Each of these units is represented by the following:



(c)




(d)



(e)

EP 0 995 786 A1




[0064] In formulae (c) through (d), R⁵², R⁵³, R⁵⁴, R⁵⁵, R⁵⁶ and R⁵⁷ may be the same or different and are each independently a divalent hydrocarbon residue having 1 to 20, preferably 2 to 12 carbon atoms. R⁵² through R⁵⁷ are each preferably a straight-chain or branched alkylene group. Specific examples for R⁵⁴ are methylene, ethylene, trimethylene, tetramethylene, pentamethylene, hexamethylene and propylene groups. Specific examples of R⁵², R⁵³, R⁵⁵, R⁵⁶ and R⁵⁷ are ethylene and propylene groups. c' is an integer of 2 to 300, preferably 10 to 200. d' is an integer of 1 to 300, preferably 2 to 200. e' is an integer of 1 to 200, preferably 2 to 100. e'' is an integer of 1 to 200, preferably 2 to 200. f' is an integer of 1 to 300, preferably 10 to 200.

[0065] In formulae (c) through (f), each of the units may be the same or different. In other words, if there exists a plurality of the groups of R⁵² through R⁵⁷, the groups of each R⁵² through R⁵⁷ may be the same or different.

[0066] The polyurethane monomer of formula (10) has a molecular-average molecular weight in the range of 2,500 to 30,000, preferably 3,000 to 20,000 and has preferably 2 to 6, more preferably 2 to 4 functional groups per molecule. The polyurethane monomer of formula (10) may be prepared by any suitable conventional method.

[0067] The other eligible polymeric monomers for Component (C) are acryloyl- or methacryloyl- modified polyalkylene oxides (hereinafter referred to as modified alkylene oxides). The polyalkylene oxide encompasses mono-, di- or poly-oxides (hereinafter referred to as modified alkylene oxides). These may be used singly or in combination. It is particularly preferred to use a monofunctional modified polyalkylene oxide as an essential component in combination with a difunctional modified polyalkylene oxide and / or a polyfunctional polyalkylene oxide. It is particularly preferred to use a mixture of a monofunctional modified polyalkylene oxide and a difunctional modified polyalkylene oxide. Although not restricted, the difunctional modified polyalkylene oxide and/or the polyfunctional polyalkylene oxide should be added in a total amount of 0.1 to 20, preferably 0.5 to 10 parts by weight of 100 parts by weight of the monofunctional modified polyalkylene oxide.

[0068] The monofunctional modified polyalkylene oxide is represented by the formula



wherein R⁵⁸, R⁵⁹, R⁶⁰ and R⁶¹ are each independently hydrogen or a C₁ - C₅ alkyl group and g' is an integer of greater than 1.

[0069] In formula (18), R⁵⁸, R⁵⁹, R⁶⁰ and R⁶¹ may be the same or different and are each independently hydrogen or a C₁ - C₅ alkyl group. Specific examples of the alkyl group are methyl, ethyl, i-propyl, n-propyl, n-butyl, t-butyl and n-pentyl groups. It is preferred that R⁵⁸ is hydrogen or methyl group, R⁵⁹ is hydrogen or methyl group, R⁶⁰ is hydrogen or methyl group and R⁶¹ is hydrogen, methyl or ethyl group.


[0070] g' in formula (18) is an integer of greater than 1 and within the range of usually 1 ≤ g' ≤ 100, preferably 2 ≤ g' ≤ 50, more preferably 2 ≤ g' ≤ 30.

[0071] Specific examples of the compound of formula (18) are those having 1 to 100, preferably 2 to 50, more preferably 2 to 20 of oxyalkylene units, such as methoxypolyethylene glycol methacrylate, methoxypolypropylene glycol methacrylate, ethoxypolyethylene glycol methacrylate, ethoxypolypropylene glycol methacrylate, methoxypolyethylene glycol acrylate, methoxypolypropylene glycol acrylate, ethoxypolyethylene glycol acrylate, ethoxypolypropylene glycol acrylate and mixtures thereof.

[0072] If g' is greater than 2, the monofunctional modified polyalkylene oxide may be those having different oxy-alkylene units, that is, copolymerized oxyalkylene units which may be alternating-, block- or random- polymerized and have 1 to 50, preferably 1 to 20 oxyethylene units and 1 to 50, preferably 1 to 20 oxypropylene unit. Specific examples of such copolymers are methoxypoly(ethylene - propylene)glycol methacrylate, ethoxypoly(ethylene - propylene)glycol methacrylate, methoxypoly(ethylene - propylene)glycol acrylate, ethoxypoly(ethylene - propylene)glycol acrylate and mixtures thereof.

[0073] The difunctional modified polyalkylene oxide is represented by the formula

EP 0 995 786 A1



wherein R^{62} , R^{63} , R^{64} and R^{65} are each independently hydrogen or a $\text{C}_1 - \text{C}_5$ alkyl group and h' is an integer of greater than 1.

[0074] The polyfunctional modified polyalkylene oxide having more than 3 functional groups is represented by the formula



wherein R^{66} , R^{67} and R^{68} are each independently hydrogen or a $\text{C}_1 - \text{C}_5$ alkyl group, i' is an integer of greater than 1, j' is an integer of 2 to 4 and L is a connecting group of valence indicated by q .

[0075] In formula (19), R^{62} , R^{63} , R^{64} and R^{65} may be the same or different and are each independently hydrogen or a $\text{C}_1 - \text{C}_5$ alkyl group. Specific examples of the alkyl group are methyl, ethyl, i-propyl, n-propyl, n-butyl, t-butyl and n-pentyl groups. It is preferred that R^{62} is hydrogen or methyl group, R^{63} is hydrogen or methyl group, R^{64} is hydrogen or methyl group and R^{65} is hydrogen, methyl or ethyl group.

[0076] h' in formula (19) is an integer of greater than 1 and within the range of usually $1 \leq h' \leq 100$, preferably $2 \leq h' \leq 50$, more preferably $2 \leq h' \leq 30$.

[0077] Specific examples of the compound of formula (19) are those having 1 to 100, preferably 2 to 50, more preferably 2 to 20 of oxyalkylene units, such as polyethylene glycol dimethacrylate, polypropylene glycol dimethacrylate, polyethylene glycol methacrylate, polypropylene glycol dimethacrylate, and mixtures thereof.


[0078] If h' is greater than 2, the difunctional modified polyalkylene oxide may be those having different oxyalkylene units, that is, copolymerized oxyalkylene units which may be alternating-, block- or random- polymerized and have 1 to 50, preferably 1 to 20 oxyethylene units and 1 to 50, preferably 1 to 20 oxypropylene unit. Specific examples of such copolymers are poly(ethylene - propylene)glycol dimethacrylate, poly(ethylene - propylene)glycol diacrylate and mixtures thereof.

[0079] R^{66} , R^{67} and R^{68} in formula (20) are each independently hydrogen or a $\text{C}_1 - \text{C}_5$ alkyl group. Specific examples of the alkyl group are methyl, ethyl, i-propyl, n-propyl, n-butyl, t-butyl and n-pentyl groups. R^{66} , R^{67} and R^{68} are each preferably hydrogen or methyl group.

[0080] i' in formula (20) is an integer of greater than 1 and within the range of usually $1 \leq i' \leq 100$, preferably $2 \leq i' \leq 50$, more preferably $2 \leq i' \leq 30$.



[0081] j' denotes a number of connecting group "L" and is an integer of $2 \leq j' \leq 4$.

[0082] Connecting group "L" is a divalent, trivalent or quadravalent hydrocarbon group having 1 to 30, preferably 1 to 20 carbon atoms. The divalent hydrocarbon group may be alkylene, arylene, arylalkylene and alkylarylene groups and hydrocarbon groups having those groups as a base skeleton. Specific examples of the divalent hydrocarbon group are methylene group, ethylene group and a group represented by




EP 0 995 786 A1

Bz represent a benzene ring). The trivalent hydrocarbon may be alkyltryl, aryltryl, arylalkyltryl, alkylaryltryl and hydrocarbon groups having those groups as the base skelton. Specific examples of the trivalent hydrocarbon group are those represented by the following formulae :




and



(Bz represents a benzene ring).

[0083] The quatravalent hydrocarbon may be alkyltetraaryl, aryltetraaryl, arylalkyltetraaryl and alkylaryltetraaryl groups and hydrocarbon groups having these groups as a base skeleton. Specific examples of the quatravalent hydrocarbon are those represented by



EP 0 995 786 A1

(Bz represents a benzene ring) .

[0084] Specific examples of the compound of formula (20) are those having 1 to 100, preferably 2 to 50, more preferably 1 to 20 oxyalkylene units, such as trimethylolpropanetri(polyethylene glycol acrylate), trimethylolpropanetri (polyethylene glycol methacrylate), trimethylolpropanetri (polypropylene glycol acrylate), trimethylolpropanetri (polypropylene glycol methacrylate), tetramethylolmethanetetra(polyethylene glycol acrylate), tetramethylolmethanetetra (polyethylene glycol methacrylate), tetramethylolmethanetetra(polypropylene glycol acrylate), tetramethylolmethanetetra(polypropylene glycol methacrylate), 2,2-bis[4-(acryloxyethoxy)phenyl]propane, 2,2-bis[4-(methacryloxyethoxy)phenyl]propane, 2,2-bis[4-(acryloxyisopropoxy)phenyl]propane, 2,2-bis[4-(methacryloxyisopropoxy)phenyl]propane and mixtures thereof.

[0085] If n in formula (20) is greater than 2, the compound may be those having different oxyalkylene units from each other, that is, copolymerized oxyalkylene units which result from alternating-, block- or random- copolymerization. Specific examples of such compounds of formula (20) having 1-50, preferably 1-20 of oxyethylene units and 1-50, preferably 1-20 of oxypropylene units are trimethylolpropanetri(poly(ethylene - propylene)glycol acrylate), trimethylolpropanetri(poly(ethylene - propylene)glycol methacrylate), tetramethylolmethanetetra(poly(ethylene - propylene)glycol acrylate) and mixtures thereof.

[0086] There may be used the difunctional modified polyalkyleneoxide of formula (19) and the polyfunctional modified polyalkyleneoxide of formula (20) in combination. When these compounds are used in combination, the weight ratio of these compounds is within the range of 0.01 / 99.9 - 99.9 / 0.01, preferably 1 / 99 - 99 / 1, more preferably 20 / 80 - 80 / 20.

[0087] The other component of Component (C) is a supporting electrolyte which may be salts, acids and alkalis.

[0088] Salts may be inorganic ion salts such as alkali metal salts and alkaline earth metal salts, quaternary ammonium salts and cyclic quaternary ammonium salts. Specific examples of such salts are alkali metal salts of lithium, sodium or potassium, such as LiClO_4 , LiSCN , LiBF_4 , LiAsF_6 , LiCF_3SO_3 , LiPF_6 , LiI , NaI , NaSCN , NaClO_4 , NaBF_4 , NaAsF_6 , KSCN and KCl , quaternary ammonium salts such as $(\text{CH}_3)_4\text{NBF}_4$, $(\text{C}_2\text{H}_5)_4\text{NBF}_4$, $(n\text{-C}_4\text{H}_9)_4\text{NBF}_4$, $(\text{C}_2\text{H}_5)_4\text{NBR}$, $(\text{C}_2\text{H}_5)_4\text{NClO}_4$ and $(n\text{-C}_4\text{H}_9)_4\text{NClO}_4$ and mixtures thereof.

[0089] Acids may be inorganic acids or organic acids. Specific examples of the acids are sulfuric acid, hydrochloric acid, phosphoric acids, sulfonic acids and carboxylic acids.

[0090] Eligible alkalis are sodium hydroxide, potassium hydroxide and lithium hydroxide.

[0091] The precursor of a polymeric solid electrolyte referred to as Component (C) is preferably prepared by using a solvent in addition to the above-described polymeric monomer and supporting electrolyte.

[0092] Eligible solvents are organic polar solvents such as methanol, ethanol, propylene carbonate, ethylene carbonate, dimethylsulfoxide, dimethoxyethane, acetonitrile, *n*-butyrolactone, sulfolan, dimethylformamide, dimethoxyethane, tetrahydrofuran, propionitrile, glutaronitrile, adiponitrile, methoxyacetonitrile, dimethylacetamide, methylpyrrolidinone, dimethylsulfoxide, dioxolane, trimethylphosphate and polyethylene glycol. Preferred are propylene carbonate, ethylene carbonate, dimethylsulfoxide, dimethoxyethane, acetonitrile, *n*-butyrolactone, sulfolan, dioxolane, dimethylformamide, tetrahydrofuran, adiponitrile, methoxyacetonitrile, dimethylacetamide, methylpyrrolidinone, dimethylsulfoxide, trimethylphosphate and polyethylene glycol. These organic polar solvents may be used singly or in combination.

[0093] The solvent is added in an amount of 50 to 1,200, preferably 100 to 900, more preferably 200 to 500 parts by weight, per 100 parts by weight of the polymeric monomer. The supporting electrolyte is added in an amount of 0.1 to 30, 1 to 20 weight percent of the solvent.

[0094] When the polyurethane monomer of formula (10) is used, the solvent is used in an amount of 100 to 1,200 parts by weight, per 100 parts by weight of the polyurethane monomer. When the modified polyalkyleneoxide of formula (18), (19) or (20), the solvent is used in amount of 50 to 800, preferably 100 to 500 parts by weight, per 100 parts by weight of the modified polyalkyleneoxide.

[0095] When the modified polyalkyleneoxide is used, the supporting electrolyte is used in an amount of 1 to 30, preferably 3 to 20 weight percent, of the total weight of the modified polyalkyleneoxide and the solvent.

[0096] If necessary, optional components may be added to Component (C) to an extent that the achievement of the purpose of the present invention is not hindered. Such optional components may be polymerization initiator such as photo polymerization initiators and thermal polymerization initiators, cross linking agents, polymers, gelatinizers and other polymeric solid electrolytes.

[0097] Eligible photo polymerization initiators are 1-(4-isopropylphenyl)-2-hydroxy-2-methylpropane-1-on. The photo polymerization initiator is used in an amount of 0.1 to 10, preferably 0.1 to 5 parts by weight, per 100 parts by weight of the polymeric monomer. The thermal polymerization initiator is used in an amount of 0.1 to 10, preferably 0.1 to 5 parts by weight, per 100 parts by weight of the polymeric monomer.

[0098] Eligible polymers are polyacrylonitrile, carboxymethyl cellulose, poly vinyl chloride, polyethylene oxide, polyurethane, polyacrylate, polymethacrylate, polyamide, polyacrylamide, cellulose, polyester, polypropylene oxide and nafion.

EP 0 995 786 A1

[0099] Eligible gelatiners are oxyethylene methacrylate, oxyethylene acrylate, urethaneacrylate, acrylicamide and agar-agar.

[0100] Eligible polymeric solid electrolytes are polyethylene oxide, a polymer of oxyethylenemethacrylate, nafion, polystyrene sulfonate, Li_3N , $\text{Na-}\beta\text{-Al}_2\text{O}_3$, $\text{Sn}(\text{HPO}_4)_2 \cdot \text{H}_2\text{O}$. Particularly preferred are polymeric solid electrolyte obtained by polymerizing an oxyalkylene(metha)acrylate-based compound or a urethane acrylate-based compound.

[0101] The blend ratio between Components (A), (B) and (C) will be described hereinbelow.

[0102] Although the blend ratio of each component is arbitrary selected, the amount of Component (A) is preferably selected to an extent that the molar ratio of the polymeric monomer contained in Component (C) to Component (A) (the bipyridinium compound) is maintained to be 10,000 / 1 to 1 / 1, preferably 1,000 / 1 to 5 / 1, more preferably 100 / 1 to 1 / 1.



[0103] If the polymeric monomer in Component (C) is the polyfunctional polyalkylene oxide, the weight ratio of Component (A) to the polyfunctional polyalkylene oxide is within the range of 1 / 0.001 to 1 / 1, particularly preferably 1 / 0.05 to 1 / 0.5.

[0104] Component (B) is used in an amount of 1 to 500, preferably 5 to 200, more preferably 10 to 100 millimole.



[0105] The term "ultraviolet absorbing compound having an ethylenic double bond" used herein denotes an ultraviolet absorbing compound into which a group having an ethylenic double bond, typically an acryloyl group or a methacryloyl group is introduced (hereinafter referred to as Component (D)).

[0106] Although Component (D) is not an essential component of the present invention, the use of Component (D) can prevent the inventive device from deteriorating in electrochromic properties caused by ultraviolet rays.

[0107] Component (D) may be a compound having a benzotriazole skeleton represented by formula (21) or (22) or a benzophenon skeleton represented by formula (23) or (24):








EP 0 995 786 A1



[0108] In formulae (21) through (24), R⁶⁹ and R⁷³ are each independently hydrogen, a halogen atom or an alkyl group having 1 to 10, preferably 1 to 6 carbon atoms. Specific examples of the halogen atom are fluorine, chlorine, bromine and iodine. Specific examples of the alkyl group are methyl, ethyl, propyl, i-propyl, butyl, t-butyl and cyclohexyl groups. R⁶⁵ and R⁷³ are usually substituted at the 4- or 5- position of the benzotriazole ring but the halogen atom and the alkyl group are usually located at the 4- position. R⁷⁰ and R⁷⁴ are hydrogen or an alkyl group having 1 to 10, preferably 1 to 6 carbon atoms. Specific examples of the alkyl group are methyl, ethyl, propyl, i-propyl, butyl, t-butyl and cyclohexyl groups. R⁷¹, R⁷⁵, R⁸⁶ and R⁸⁹ are each independently a C₁ - C₁₀ alkylene group such as ethylene and trimethylene groups. R⁸⁰ and R⁸² each independently indicate a covalent bond or are a C₁ - C₁₀ alkylene group such as ethylene and trimethylene groups. R⁷², R⁷⁷, R⁸¹, R⁸³, R⁸⁸ and R⁹¹ are each independently hydrogen or methyl group. R⁷⁶, R⁸⁷ and R⁹⁰ are each independently a C₁ - C₁₀ alkylene group such as methylene group. m, n, p, r, s, t, u, x and y are each an integer of 0 or 1 and satisfy the conditions of 1 ≤ m + n ≤ 2, 1 ≤ r + s ≤ 2, 1 ≤ t + u ≤ 2 and 1 ≤ x + y ≤ 2. p, q, v and w are each an integer of 0 ≤ p ≤ 3, 0 ≤ q ≤ 3, 0 ≤ v ≤ 3 and 0 ≤ w ≤ 3.




[0109] Specific examples of preferred compounds for Component (D) are as follows and two or more of these compounds may be used in combination:

EP 0 995 786 A1



55

EP 0 995 786 A1



[0110] Component (D) is used in an amount of 1 to 500, preferably 5 to 200, more preferably 10 to 100 millimole, per mole of the polymeric monomer in Component (C).

[0111] Without using Component (D), it is possible to impart the inventive device with stability against ultraviolet rays by the following method:

- (1) mixing a composition containing Components (A), (B) and (C) with an ultraviolet absorbing agent before curing the composition to form an ion conductive layer; and
- (2) providing an ultraviolet absorbing layer at any site of the electrochromic device.


[0112] When method (1) is employed, the ultraviolet absorbing agent is used in an amount of 0.05 to 40, preferably 0.5 to 20 mass percent of Component (C).

[0113] In the case of employing method (2), the ultraviolet absorbing layer may be arranged in any location of the device. For instance, the ultraviolet absorbing layer may be arranged on the outermost surface of the device through which light passes through or between the substrate and the electrode located at the side of the device subjected to light. The ultraviolet absorbing layer may be formed by any suitable method. For instance, the ultraviolet absorbing layer may be formed by applying an ultraviolet absorbing agent dissolved in a solvent at a selected position and then

EP 0 995 786 A1

distilling out the solvent. Eligible ultraviolet absorbing agents for methods (1) and (2) are compounds having a benzotriazole skeleton or a benzophenone skeleton.



[0114] Preferred examples of the compound having a benzotriazole skeleton are those represented by the formula



[0115] In formula (25), R^{92} is hydrogen, a halogen atom or an alkyl group having 1 to 10, preferably 1 to 6 carbon atoms. The halogen atom may be fluorine, chlorine, bromine and iodine. Specific examples of the alkyl group are methyl, ethyl, propyl, i-propyl, butyl, t-butyl and cyclohexyl groups. R^{93} is hydrogen or an alkyl group having 1 to 10, preferably 1 to 6. Specific examples of the alkyl group are methyl, ethyl, propyl, i-propyl, butyl, t-butyl and cyclohexyl groups. R^{94} is an alkylene group having 1 to 10, preferably 1 to 3 carbon atoms or an alkylidene having 1 to 10, preferably 1 to 3 carbon atoms. Specific examples of the alkylene group are methylene, ethylene, trimethylene and propylene. Specific examples of the alkylidene are ethylidene and propylidene.

[0116] Specific examples of the compound of formula (25) are 3-(5-chloro-2H-benzotriazole-2-yl)-5-(1,1-dimethylethyl)-4-hydroxybenzene propanoic acid, 3-(2H-benzotriazole-2-yl)-5-(1,1-dimethylethyl)-4-hydroxybenzene ethanoic acid, 3-(2H-benzotriazole-2-yl)-4-hydroxybenzene ethanoic acid and 3-(5-methyl-2H-benzotriazole-2-yl)-5-(1-methylethyl)-4-hydroxybenzene propanoic acid.

[0117] Preferred examples of the compound having a benzophenone skeleton are those represented by the formula



[0118] In the above formulae, R^{96} and R^{97} may be the same or different and are each independently a hydroxyl group, an alkyl or alkoxy group having 1 to 10, preferably 1 to 6 carbon atoms. m' and n' are an integer of $0 \leq m' \leq 3$ and $0 \leq n' \leq 3$. Specific examples of the alkyl group are methyl, ethyl, propyl, i-propyl, butyl, t-butyl and cyclohexyl groups. Specific examples of the alkoxy group are methoxy, ethoxy, propoxy, i-propoxy and butoxy groups. R^{96} is an alkylene group having 1 to 10, preferably 1 to 3 carbon atoms or an alkylidene having 1 to 10, preferably 1 to 3 carbon atoms. Specific examples of the alkylene group are methylene, ethylene, trimethylene and propylene. Specific examples of the alkylidene are ethylidene and propylidene.

[0119] Specific examples of the compound having a benzophenone skeleton are 2-hydroxy-4-methoxybenzophenone-5-carboxylic acid, 2,2'-dihydroxy-4-methoxybenzophenone-5-carboxylic acid and 4-(2-hydroxybenzoyl)-3-hydroxybenzene propanoic acid.

EP 0 995 786 A1

[0120] The electrochromic device according to the present invention comprises a pair of electrically conductive substrates and an ion conductive layer disposed therebetween which layer is obtained by curing a composition containing Components (A) through (C) and Component (D) if necessary. The term "curing" used herein denotes an increase in viscosity brought by chemical reaction. Such chemical reaction may be thermal- or photo- polymerization, polycondensation and cross linking, among which thermal- or photopolymerization is preferred.

[0121] In the case of photo polymerization, a photo polymerization initiator is preferably added to Component (C). The type and source of light are not particularly restricted. Preferred types of light are far ultraviolet rays, ultraviolet rays and visible rays. Preferred light sources are high voltage mercury lamps, fluorescent lights and xenon lamps. Although not restricted, the photo polymerization is conducted by irradiating light at 100 to 50,000, preferably 1,000 to 20,000 mJ / cm².

[0122] In the case of thermal polymerization, a thermal polymerization initiator is preferably added to Component (C). Although not restricted, thermal polymerization is conducted at a temperature of 0 to 130 °C, 20 to 80 °C and for 10 minutes to 100 hours, preferably 30 minutes to 40 hours.

[0123] The progress of the reaction can be observed by detecting a decrease in double bond with IR or NMR.

[0124] Although not restricted, the resulting ion conductive layer has preferably an ion conductivity of greater than 1 x 10⁻⁷, preferably greater than 1 x 10⁻⁶, more preferably greater than 1 x 10⁻⁷ S/cm, at room temperature. Although not restricted, the ion conductive layer has a thickness of 1 μ to 3 mm, preferably 10 μ to 1mm.

[0125] The ion conductive layer may be formed by any suitable known method. For instance, the ion conductive layer may be formed by curing a composition containing Components (A) through (C) or (A) through (D) alternatively with optional components after being injected into a space between two electrically conductive substrates disposed in opposed relation and having sealed peripheral edges, by vacuum injection or atmospheric injection or a meniscus method. Alternatively, after the ion conductive layer is formed over the electrode of one electrically conductive substrate, this substrate is assembled with the other electrically conductive substrate.

[0126] The electrochromic device according to the present invention is characterized by having two electrically conductive substrates at least one of which is transparent and an ion conductive material layer disposed therebetween. The basic structure of the device will be described hereinbelow with reference to the annexed drawings.

[0127] Fig. 1 shows a device 10 composed of a transparent electrically conductive substrate 11 having a transparent substrate 12 and a transparent electrode layer 13 laminated thereover, an opaque, transparent or reflective electrically conductive substrate 14 having a transparent or opaque substrate 17 and a transparent, opaque or reflective electrode layer 16 disposed thereover and an ion conductive material layer 14 disposed between the electrically conductive substrates 11, 17.

[0128] Fig. 2 shows the structure of an display device or a smart window 10 in which an ion conductive material layer 14 is disposed between two transparent electrically conductive substrates 11, 15 each of which has a transparent substrate 12 and a transparent electrode layer 13 formed over one surface of each the substrate 11, and which are placed at a certain interval so that the transparent electrode layers face each other.

[0129] Fig. 3 show the structure of an electrochromic mirror 10 in which an ion conductive material layer 14 is disposed between a transparent electrically conductive substrate 11 having a transparent substrate 12 over one of which surface a transparent electrode layer 13 is formed and a reflective electrically conductive substrate 15 having a transparent substrate 12 over one surface of which a transparent electrode layer 13 is formed and over the other surface of which a reflective layer 19 is formed, the electrically conductive substrates being placed at a certain interval so that the transparent electrode layers face each other.

[0130] The layers forming the device according to the present invention may be prepared by following the above-described methods. For instance, in the case of the device shown in Fig. 1, Laminate (A) is obtained by forming a transparent electrode layer 13 over a transparent substrate 12 in the foregoing manner and apart from this Laminate (B) is obtained by a transparent, opaque or reflective electrode layer 16 over a substrate 17. Consequently, Laminates (A) and (B) are placed in a opposing relation to each other with a space of 1 to 1,000 μm and then the peripheral edges except a portion for injecting an ion conductive material are sealed with a sealant 18 thereby producing a hallow cell with an injection port. After injecting a composition containing Components (A) through (C) and Component (D) added as required into the cell thorough the injecting port, an ion conductive material layer 16 is formed by curing the composition thereby producing a device 10.

[0131] A spacer may be used in order to keep the space between Laminates (A) and (B) constant upon placing them in an opposing relation. The spacer may be in the form of beads or sheet formed from glass or polymer. The spacer may be provided by inserting the beads or sheet into the space of the substrates facing each other or by forming protrusions formed from an insulate material such as a resin, over the electrode of the electrically conductive substrate.

[0132] Although no particular limitation is imposed on a method of curing a composition containing Components (A) through (C) or Components (A) through (D), the composition may be cured by light or heat or by mixing a reactive liquid curing with a lapse of time with the composition immediately before injecting the same. The injection port may be sealed in any suitable manner.

EP 0 995 786 A1

[0133] Alternatively, Laminate (A') is obtained by forming a transparent electrode layer 13 and an ion conductive material layer 14 in this order over a transparent substrate 12 in the aforesaid manner and apart from this Laminate (B') is obtained by forming an opaque or transparent reflective electrode layer 16 over a substrate 17 in the aforesaid manner. Consequently, Laminates (A') and (B') are placed in an opposing relation with a space of 1 to 1,000 μm so that the ion conductive material layer 14 is contacted with the reflective electrode layer, followed by sealing the peripheral edges with a sealant 18.

[0134] In the case of the electrochromic dimmer glass shown in Fig.2, after two transparent electrically conductive substrates 11, 15 are each prepared by forming a transparent electrode layer 13 over one surface of a transparent substrate 12, the dimmer glass is produced by following the procedure as described with respect to the device of Fig. 1. In the case of the electrochromic mirror shown in Fig. 3, after preparing a transparent electrically conductive substrate by forming a transparent electrode layer 13 over one surface of a transparent substrate 12 and a reflective electrically conductive substrate by forming a transparent electrode layer 13 over one surface of a transparent substrate 12 and a reflective layer 19 over the other surface of the same, the electrochromic mirror is produced by following the procedure as described with respect to the device of Fig. 1.

[0135] The typical examples of structures of the devices according to the present invention are as shown in Figs. 1 to 3. However, the present invention is not restricted to these particular embodiments and thus may further contain other components. Such components are exemplified by an ultraviolet shielding layer such as an ultraviolet reflective layer and an ultraviolet shielding layer and an overcoat layer for protecting the whole mirror layer or each layer of an electrochromic mirror. Such an ultraviolet shielding layer may be arranged the out side or the transparent electrode layer side of a transparent substrate 12. Such an overcoat layer may be arranged over the outer side of an transparent substrate 12 or a reflective layer 19.


[0136] The device according to the present invention is useful as display devices, smart windows, anti-glare mirrors for automobiles or decorative mirrors for indoor use.

[0137] The examples which follow are intended as an illustration of certain preferred embodiments of the present invention, and no limitation of the invention is implied.

Example 1

(1) Synthesis of Bipyridinium Compound

[0138] Bipyridine was reacted with an equimolar amount of benzylchloride in acetone thereby obtaining N-benzylbipyridiniumchloride. 5.94 g (21 mmol) of the N-benzylbipyridiniumchloride thus obtained were dissolved in 150 ml of 2-propanol and then 3.21 g (21 mmol) of chloromethyl styrene (m- and p- isomers mixture) were added thereto, followed by 24-hour stirring at room temperature thereby obtaining N-benzyl-N'-vinylbenzylbipyridinium chloride represented by the formula




(2) Synthesis of Amine Compound

[0139] 25.4 g (150 mmol) of diphenylamine and 22.8 g (150 mmol) of cesium fluoride were weighed into a 500 ml three-necked flask. After substituting the flask with nitrogen, 250 ml of dimethylsulfoxide was added to the mixture and then stirred. 21.3 g (150 mmol) of 1-fluoro-4-nitrobenzene was then added to the mixture and heated at a temperature of 120 $^{\circ}\text{C}$ in an oil bath, followed by 24-hour stirring.


[0140] The resulting reaction solution was poured into ice-cold water to be precipitated. The solid thus obtained was recrystallized from acetic acid thereby obtaining 29.5 g (102 mmol) of a compound represented by the formula

EP 0 995 786 A1




[0141] 15.0 g (52 mmol) of the compound of formula (31) were transferred to a 500 ml three-necked flask and supplied with hydrogen at atmospheric pressure after adding 200 ml of dimethylformamide and 1.5 g of 5% palladium / carbon mixture. After 12-hour stirring at room temperature, the palladium carbon was filtered out and then the reaction solution was poured into ice-cold water to be precipitated.

[0142] A white solid substance was vacuum-dried thereby obtaining 12.5 g (48 mmol) compound represented by the formula



[0143] 12.5 g (48 mmol) of the compound of formula (32) were transferred to a 500 ml three-necked flask and then stirred under ice cooling after adding dropwise a 20 ml solution of 6.3 g of chloride methacrylate and benzene.

[0144] The reaction solution was washed with a 1 NHCl aqueous solution, water and a 1 NNaOH aqueous solution, twice respectively and dried over sodium sulfate. The solvent was removed thereby obtaining 13.4 g (41 mmol) compound represented by the formula






EP 0 995 786 A1

(3) Synthesis of Ultraviolet Absorbing Compound Having an Ethylenic Double Bond

[0145] To a 300 ml three-necked flask was charged with 18.3 g (49 mmol) compound of formula (34) shown below, 60 ml of diglyme (diethylene glycol dimethyl ether) and 0.9 g (7 mmol) of dimethylbenzylamine. A solution obtained by dissolving 7.7 g (54 mmol) of glycidyl methacrylate in 20 ml diglyme was added dropwise to the mixture and then reacted by heating for 13 hours. Even after cooling the resulting solution, it is observed that the solution had no insoluble substance and was transparent.

[0146] The solution was poured into methanol to be precipitated. The solid substance thus obtained was vacuum-dried thereby obtaining 18.9 g (37 mmol) of a compound represented by formula (36) shown in below.



(4) Production of Electrochromic Mirror

[0147] A laminate was prepared by forming a thin film of palladium as a highly reflective electrode, over a substrate. An epoxy sealant was applied in the form of lines along the peripheral edges, except for a portion to be used for injecting an electrolyte precursor solution, of the palladium film layer of the laminate. A transparent glass substrate coated with SnO_2 was superposed over the laminate such that the SnO_2 surface and the palladium film layer face each other and then the epoxy sealant was cured with pressurizing thereby producing a hallow cell with an injection port.

[0148] On the other hand, a homogenous solution was obtained by adding 0.4 g of lithium perchlorate to 4.0 g of a mixed solution of 1.0 g of methoxypolyethylene glycol monomethacrylate (the number of oxyethylene unit: 4) manufactured by SHIN NAKAMURA CHEMICAL CO. LTD. under the trade name of ME04, 0.02 g of polyethylene glycol dimethacrylate (the number of oxyethylene unit: 9) manufactured by SHIN NAKAMURA CHEMICAL CO. LTD. under the trade name of 9G and 4.0 g of γ -butyrolactone. To the homogenous solution was added 0.02 g of a photopolymerization initiator, 1-(4-isopropylphenyl)-2-hydroxy-2-methylpropane-1-on manufactured by MELK CO., LTD. under the trade name of "Dicure-1116" in a dark room and further added 0.85 g (1.84 mmol) of N-benzyl-N'-vinylbenzylbipyridinium chloride obtained in the above procedure (1), 0.60 g (1.84 mmol) of the amine compound of formula (33) and 0.95 g (1.84 mmol) of the ultraviolet absorbing compound having an ethylenic double bond of formula (36). The resulting homogenous solution was injected into the cell obtained above after being dehydrated.

[0149] After the injection port was sealed with an epoxy sealant, the solution in the cell was cured by exposing the

EP 0 995 786 A1

side of the transparent substrate of the cell to fluorescent light thereby obtaining an electrochromic polymeric solid electrolyte and also an all solid type electrochromic mirror of the structure as shown in Fig. 3.

[0150] The mirror when assembled was not colored and had a reflectance of about 80 %. The mirror was quick in response to an electric voltage and exhibited excellent electrochromic properties. The mirror was colored upon application of a voltage of 1.2 V and had a reflectance of 10 %. Coloring and bleaching operations were repeated every 10 seconds, but no remnant coloration was observed after the lapse of about 200 hours.

[0151] When the electrochromic mirror was broken, no medium scattered and flowed out.

[0152] 50 mJ/cm² of xenon light was irradiated to the electrochromic mirror when it was colored by applying a voltage of 1.2 V. After terminating the application of the voltage, the reflectance of the mirror was recovered from 10 % to 80%.


As a result of this, the electrochromic device using the polymeric solid electrolyte according to the present invention is superior in resistance to deterioration against ultraviolet rays.

Example 2

(1) Synthesis of Bipyridinium Compound

[0153] 3.12 g (20 mmol) of bipyridyl was dissolved in 100 ml of acetonitrile in a flask, followed by addition of 6.10 g (40 mmol) of chloromethyl styrene (m- and p- isomers mixture) and 50 mg (0.45 mmol) of an polymerization prohibitor, hydroquinone.

After stirring the mixture at room temperature for 24 hours, the solid substance was filtered and dried thereby obtaining 7.84 g (17 mmol) of N,N'-divinylbenzylbipyridinium dichloride represented by the formula



(2) Production of Electrochromic Smart Window

[0155] An electrically conductive substrate was prepared by coating the surface of a transparent glass substrate with ITO. An epoxy sealant was applied in the form of lines along the peripheral edges, except for a portion to be used for injecting an electrolyte precursor solution, of the ITO layer of the substrate. A transparent glass substrate coated with platinum was superposed over the ITO coated substrate such that the ITO surface and the platinum surface face each other and then the epoxy sealant was cured with pressurizing thereby producing a hallow cell with an injection port.

[0156] On the other hand, a homogenous solution was obtained by adding 0.4 g of lithium perchlorate to 4.0 g of a mixed solution of 1.0 g of methoxypolyethylene glycol monomethacrylate (the number of oxyethylene unit: 4) manufactured by SHIN NAKAMURA CHEMICAL CO. LTD. under the trade name of M40GN, 0.02 g of polyethylene glycol dimethacrylate (the number of oxyethylene unit: 9) manufactured by SHIN NAKAMURA CHEMICAL CO. LTD. under the trade name of 9G and 4.0 g of γ -butyrolactone. To the homogenous solution was added 0.02 g of a photopolymerization initiator, 1-(4-isopropylphenyl)-2-hydroxy-2-methylpropane-1-on manufactured by MELK CO., LTD. under the trade name of "Diecure-1116" in a dark room and further added 0.85 g (1.84 mmol) of N,N'-di-vinylbenzylbipyridinium dichloride of formula (39) obtained the above procedure (1), 0.60 g (1.84 mmol) of the amine compound of formula (33) in Example 1 and 1.20 g (2.33 mmol) of the ultraviolet absorbing compound having an ethylenic double bond of formula (36) in Example 1. The resulting homogenous solution was injected into the cell obtained above after being dehydrated.

[0157] After the injection port was sealed with an epoxy sealant, the solution in the cell was cured by exposing both the surfaces of the cell to fluorescent light thereby obtaining an electrochromic polymeric solid electrolyte and also an all solid type electrochromic smart window as shown in Fig. 1.

[0158] The smart window when assembled was not colored and had a reflectance of about 90 %. The mirror was quick in response to an electric voltage and exhibited excellent electrochromic properties. The mirror was colored upon application of a voltage of 1.2 V and had 10 % transmittance of 633 nm wavelength light. Coloring and bleaching operations were repeated every 10 seconds, but no remnant coloration was observed after the lapse of about 200 hours.

[0159] When the electrochromic smart window was broken, no medium sandwiched between the substrates scattered and flowed out.


EP 0 995 786 A1

[0160] 50 mJ/cm² of xenon light was irradiated to the electrochromic mirror when it was colored by applying a voltage of 1.2 V. After terminating the application of the voltage, the reflectance of the smart window was recovered from 20 % to 90%. As a result of this, it is apparent that the electrochromic device using the polymeric solid electrolyte according to the present invention is superior in resistance to deterioration against ultraviolet rays.

Example 3



(1) Synthesis of Bipyridinium Compound

[0161] N-benzyl-N'-vinylbenzylbipyridinium chloride was recovered from a mixed solution of water-IPA containing HBF₄ so as to be anion-exchanged thereby obtaining N-benzyl-N'-vinylbenzylbipyridinium-di(tetrafluoroborate) represented by the formula



(2) Synthesis of Amine Compound

[0162] To 10.0 g (39.9 mmol) of dihydro-di-(2-hydroxyethyl)phenazine represented by formula (39) below dissolved in 30 ml of methylene chloride was added dropwise a solution of 6.3 g (60 mmol) chloride methacrylate / 15 ml methylene chloride. After stirring at room temperature for 5 hours, the solution was washed with aqueous solution containing dilute sodium chloride, dilute hydrochloric acid and dilute sodium hydrogencarbonate, respectively and dried over NaSO₄. The methylene chloride was distilled off thereby obtaining 11.9 g (29.3 mmol) of a compound represented by formula (40):



EP 0 995 786 A1

(3) Production of Electrochromic Mirror

[0163] A laminate was prepared by forming a thin film of palladium as a highly reflective electrode, over a substrate. An epoxy sealant was applied in the form of lines along the peripheral edges, except for a portion to be used for injecting an electrolyte precursor solution, of the palladium film layer of the laminate. A transparent glass substrate coated with ITO was superposed over the laminate such that the ITO surface and the palladium film layer face each other and then the epoxy sealant was cured with pressurizing thereby producing a hallow cell with an injection port.

[0164] On the other hand, a homogenous solution was obtained by adding 0.4 g of lithium perchlorate to 4.0 g of a mixed solution of 1.0 g of methoxypolyethylene glycol monomethacrylate (the number of oxyethylene unit: 4) manufactured by SHIN NAKAMURA CHEMICAL CO. LTD. under the trade name of M40GN, 0.02 g of polyethylene glycol dimethacrylate (the number of oxyethylene unit: 9) manufactured by SHIN NAKAMURA CHEMICAL CO. LTD. under the trade name of 9G and 4.0 g of γ -butyrolactone. To the homogenous solution was added 0.02 g of a photopolymerization initiator, 1-(4-isopropylphenyl)-2-hydroxy-2-methylpropane-1-on manufactured by MELK CO., LTD. under the trade name of "Diecure-1116" in a dark room and further added 0.87 g (1.85 mmol) of N-benzyl-N'-vinylbenzylbipyridinium-di(tetrafluoroborate) obtained in the above procedure (1), 0.75 g (1.85 mmol) of the amine compound of formula (40) and 0.95 g (1.84 mmol) of the ultraviolet absorbing compound having an ethylenic double bond of formula (36). The resulting homogenous solution was injected into the cell obtained above after being dehydrated.

[0165] After the injection port was sealed with an epoxy sealant, the solution in the cell was cured by exposing the side of the transparent substrate of the cell to fluorescent light thereby obtaining an electrochromic polymeric solid electrolyte and also an all solid type electrochromic mirror of the structure as shown in Fig. 3.

[0166] The mirror when assembled was not colored and had a reflectance of about 80 %. The mirror was quick in response to an electric voltage and exhibited excellent electrochromic properties. The mirror was colored upon application of a voltage of 1.0 V and had a reflectance of about 8 %. Coloring and bleaching operations were repeated every 10 seconds, but no remnant coloration was observed after the lapse of about 200 hours.

[0167] When the electrochromic mirror was broken, no medium sandwiched between the substrates scattered and flowed out.

[0168] 50 mJ/cm² of xenon light was irradiated to the electrochromic mirror when it was colored by applying a voltage of 1.2 V. When the application of the voltage was terminated, the reflectance of the mirror was recovered from 8 % to 80% after 10 seconds passed. As a result of this, the electrochromic device using the polymeric solid electrolyte according to the present invention is superior in resistance to deterioration against ultraviolet rays.

Comparative Example 1

[0169] A laminate was prepared by forming a thin film of palladium as a highly reflective electrode, over a substrate. An epoxy sealant was applied in the form of lines along the peripheral edges, except a portion to be used for injecting an electrolyte precursor solution, of the palladium film layer of the laminate. A transparent glass substrate coated with SnO₂ was superposed over the laminate such that the SnO₂ surface and the palladium film layer face each other and then the epoxy sealant was cured with pressurizing thereby producing a hallow cell with an injection port.

[0170] On the other hand, a homogenous solution was prepared by adding 0.4 g of lithium perchlorate to 4.0 g of propylene carbonate. To the homogenous solution were added 0.95 g (1.84 mmol) of N,N'-diheptylbipyridinium bromide and N,N,N',N'-tetramethylphenylenediamine. The resulting homogenous solution was injected into the cell through the port after being dehydrated.

[0171] The mirror when assembled was not colored and had a reflectance of about 80 %. The mirror was quick in response to an electric voltage and exhibited excellent electrochromic properties. The mirror was colored upon application of a voltage of 1.0 V and had a reflectance of about 10 %. However, after coloring and bleaching operations were repeated every 10 seconds, blue remnant coloration around the sealant was observed after the elapse of about 200 hours, which remnant was believed to result from dimerization of viologen.

[0172] When the electrochromic mirror was broken, the medium sandwiched between the substrates scattered.


[0173] The electrochromic device is superior in capabilities of avoiding the viologen from precipitation caused by dimerization thereof and resulting in the deterioration of the viologen and electron donative compounds and the medium from scattering. Furthermore, the electrochromic device according to the present invention can avoid the viologen and electron donative compounds from deterioration caused by being exposed to ultraviolet rays, by using an ultraviolet absorbing compound.

Claims


1. An electrochromic device which has an ion conductive layer obtained by curing a composition comprising (a) a

EP 0 995 786 A1


bipyridinium compound represented by formula (1), (b) an amine compound represented by formula (2) and / or (3) and (c) a precursor component of a polymeric solid electrolyte, disposed between two electrically conductive substrates at least one of which is transparent, said formula (1) being



wherein X⁻ and Y⁻ are the same or different and are each independently a counter anion selected from the group consisting of an halogen anion, ClO₄⁻, BF₄⁻, PF₆⁻, CH₃COO⁻ and CH₃(C₆H₄)SO₃⁻, R¹ is hydrogen or a C₁ - C₅ alkyl group, R² is a C₁ - C₃₀ divalent hydrocarbon or oxygen-containing hydrocarbon group, R³ is a C₁ - C₂₀ hydrocarbon or oxygen-containing hydrocarbon group and a is an integer of 0 or 1; said formula (2) being




wherein R⁴ is hydrogen or a C₁ - C₅ alkyl group, R⁵ is a C₁ - C₁₅ hydrocarbon or oxygen-containing hydrocarbon group, b is an integer of 0 or 1, R⁶ and R⁷ are the same or different and are each independently hydrogen or a C₁ - C₂₀ hydrocarbon or oxygen-containing hydrocarbon group, R⁸ is hydrogen or a C₁ - C₂₀ hydrocarbon or oxygen-containing hydrocarbon group and Ar¹ is a C₆ - C₂₀ divalent aromatic hydrocarbon group; and said formula (3) being




wherein R⁹ is hydrogen or a C₁ - C₅ alkyl group, R¹⁰ is a C₁ - C₁₅ hydrocarbon or oxygen-containing hydrocarbon group, c is an integer of 0 or 1, R¹¹ and R¹² are the same or different and are each independently hydrogen or a C₁ - C₂₀ hydrocarbon or oxygen-containing hydrocarbon group and R¹³ is hydrogen or a C₁ - C₂₀ hydrocarbon or oxygen-containing hydrocarbon group.

2. The electrochromic device according to claim 1 which has said ion conductive layer further containing (d) an ultraviolet absorbing compound having an ethylenic double bond.
3. The electrochromic device according to claim 1 wherein said bipyridinium compound represented by formula (1) wherein R¹ is selected from the group consisting of hydrogen and methyl group, R² is selected from the group consisting of methylene, ethylene, tetramethylene, propylene, m-phenylene, p-phenylene, alkyl-substituted phenylene, biphenylene, naphthylene, oxymethylene and oxypropylene groups, R³ is selected from the group consisting of methyl, ethyl, i-propyl, n-propyl, n-butyl, t-butyl, n-pentyl, n-hexyl, cyclohexyl, n-heptyl, n-octyl, benzyl and vinylbenzyl, and groups represented by



EP 0 995 786 A1




and



said amine compound represented by formula (2) and / or (3) wherein R⁴ and R⁹ are each independently selected from the group consisting of hydrogen or methyl group, R⁵ and R¹⁰ are each independently selected from the group consisting of groups represented by




and




R⁶, R⁷, R¹¹ and R¹² are each independently selected from the group consisting of methyl, ethyl, n-propyl, i-propyl, n-butyl, i-butyl, t-butyl, hexyl, heptyl, octyl, tolyl, ethylphenyl, phenyl, methoxyphenyl and ethoxyphenyl groups, R⁸ and R¹³ are each independently selected from the group consisting of methyl, ethyl, n-propyl, i-propyl, n-butyl, i-butyl, t-butyl, hexyl, heptyl, octyl, tolyl, ethylphenyl, phenyl, methoxyphenyl and ethoxyphenyl groups, and Ar¹ is selected from the group consisting of o-phenylene, m-phenylene, p-phenylene, alkyl-substituted phenylene, bi-phenylene and naphthylene groups.

4. The electrochromic device according to claim 1 wherein said precursor component of a polymeric solid electrolyte comprises a polymeric monomer and a supporting electrolyte.
5. The electrochromic device according to claim 1 wherein said polymeric monomer is selected from the group consisting of a monofunctional modified polyalkylene oxide represented by the formula



wherein R⁵⁸, R⁵⁹, R⁶⁰ and R⁶¹ are each independently hydrogen or a C₁ - C₅ alkyl group and g' is an integer of greater than 1; a difunctional modified polyalkylene oxide represented by the formula

EP 0 995 786 A1



wherein R^{62} , R^{63} , R^{64} and R^{65} are each independently hydrogen or a $\text{C}_1 - \text{C}_6$ alkyl group and h' is an integer of greater than 1, and a polyfunctional modified polyalkylene oxide represented by the formula



wherein R^{66} , R^{67} and R^{68} are each independently hydrogen or a $\text{C}_1 - \text{C}_5$ alkyl group, i' is an integer of greater than 1, j' is an integer of 2 to 4 and L is a connecting group of valence indicated by q.

6. The electrochromic device according to claim 5 wherein said polymeric monomer contains said difunctional polyoxyalkylene oxide and / or said polyfunctional in a total amount of 0.1 to 20 part by weight, of 100 parts by weight of said monofunctional polyoxyalkylene oxide.

EP 0 995 786 A1

FIG. 1




FIG. 2





FIG. 3



EP 0 995 786 A1



European Patent
Office

EUROPEAN SEARCH REPORT

Application Number
EP 99 85 0155

DOCUMENTS CONSIDERED TO BE RELEVANT			
Category	Citation of document with indication, where appropriate, of relevant passages	Relevant to claim	CLASSIFICATION OF THE APPLICATION (Int.Cl.7)
D, X	EP 0 612 826 A (DONNELLY CORP) 31 August 1994 (1994-08-31) * page 19, line 41 - line 46; claim 3; example 29 * * page 18, line 33 - line 37 *	1-6	C09K9/02 G02F1/15
A	WO 97 30134 A (BERNETH HORST ;BAYER AG (DE); CLAUSSEN UWE (DE); HAARER DIETRICH () 21 August 1997 (1997-08-21) * example 21 *	1	
			TECHNICAL FIELDS SEARCHED (Int.Cl.7)
			C09K G02F
The present search report has been drawn up for all claims			
Place of search THE HAGUE		Date of completion of the search 2 February 2000	Examiner Shade, M
<p>CATEGORY OF CITED DOCUMENTS</p> <p>X : particularly relevant if taken alone Y : particularly relevant if combined with another document of the same category A : technological background O : non-written disclosure P : intermediate document</p> <p>T : theory or principle underlying the invention E : earlier patent document, but published on, or after the filing date D : document cited in the application L : document cited for other reasons & : member of the same patent family, corresponding document</p>			

EPH FORM 1500 03/92 (P01cat)

EP 0 995 786 A1

ANNEX TO THE EUROPEAN SEARCH REPORT
ON EUROPEAN PATENT APPLICATION NO.

EP 99 85 0155

This annex lists the patent family members relating to the patent documents cited in the above-mentioned European search report.
The members are as contained in the European Patent Office EDP file on
The European Patent Office is in no way liable for these particulars which are merely given for the purpose of information.
02-02-2000

Patent document cited in search report	Publication date	Patent family member(s)	Publication date
EP 0612826 A	31-08-1994	JP 7070218 A	14-03-1995
		US 6002511 A	14-12-1999
		US 5910854 A	08-06-1999
WO 9730134 A	21-08-1997	DE 19605451 A	21-08-1997
		CZ 9802581 A	17-03-1999
		EP 0880568 A	02-12-1998

EPO FORM P0459

For more details about this annex : see Official Journal of the European Patent Office, No. 12/82